

Investigation of Solute Diffusion through Polyvinyl Alcohol/ Polyallylamine Ultrafiltration Membrane

D. Ariono ¹

A.K. Wardani ¹

P.T.P. Aryanti ²

I.G. Wenten ^{*1,3}

¹ Department of Chemical Engineering, Institut Teknologi Bandung, Jl. Ganesha 10, Bandung, Indonesia 40132

² Department of Chemical Engineering, Universitas Jenderal Achmad Yani, Jl. Terusan Jendral Sudirman, Cimahi, Indonesia 40285

³ Research Center for Nanosciences and Nanotechnology, Institut Teknologi Bandung, Jl. Ganesha 10, Bandung 40132, Indonesia

*e-mail: igw@che.itb.ac.id

Ultrafiltration membrane has been widely used for several applications due to their high separation capacity, high selectivity, and low operating pressure. In this work, solutes diffusion through polyvinyl alcohol/polyallylamine ultrafiltration membrane was investigated. The membrane was prepared by phase inversion method with glutaraldehyde as crosslinking agent. Meanwhile, NaCl and CaCl₂ were used as solutes, either as a single or double solute. The results showed that the increase of polyallylamine concentration led to the increase of membrane swelling degree. For both single and double solutes, diffusion of Na⁺ and Ca²⁺ were slightly decreased with the increase of swelling degree. However in double solute diffusion, there was interaction between Na⁺, Ca²⁺, and membrane that made Na⁺ ions moved faster and Ca²⁺ ions moved slower compared to single solute diffusion. In addition, the increase of solute concentration led to the increase of Na⁺ diffusion coefficient and the decrease of Ca²⁺ diffusion coefficient.

Keywords: polyallylamine, polyvinyl alcohol, swelling degree, solute diffusion, ultrafiltration membrane

INTRODUCTION

Ultrafiltration (UF) membrane has been widely used in water and wastewater treatment, chemical purification, gas separation, etc. UF offers some advantages, such as energy efficiency, high separation capacity, high selectivity, and relatively low cost (Khoiruddin, Widiyasa et al. 2014, Aryanti, Yustiana et al. 2015, Himma, Anisah et al. 2016, Ariono, Aryanti et al. 2017,

Wardani, Hakim et al. 2017). Several polymers have been used to prepare ultrafiltration membrane, such as polysulfone (Hamid, Ismail et al. 2011, Aryanti, Khoiruddin et al. 2013, Wardani, Hakim et al. 2017), polyvinyl alcohol (Vauclair, Tarjus et al. 1997, Wu, Lin et al. 2006, Josh, Haik et al. 2013, Jose, Shehzad et al. 2014), polyethersulfone (Rahimpour and Madaeni 2007, Razmjou, Mansouri et al. 2011, Moghimifar, Raisi et al. 2014),

polyvinyl chloride (Aryanti, Yustiana et al. 2015), polyvinyl fluoride (Du, Peldszus et al. 2009), polyacrylonitrile (Asatekin, Kang et al. 2007), etc. Among them, polyvinyl alcohol (PVA) is one of the promising material due to its excellent properties such as film formability, barrier to gases and liquids, hydrophilicity, good adhesion to various surfaces, chemical resistance and biodegradability (Wu, Gu et al. 2012, Josh, Haik et al. 2013, Jose, Shehzad et al. 2014). Besides, PVA is a polyelectrolyte material that contains of ionic groups, thus it can be used to produce charge UF membrane.

In several cases, the existence of charge on the membrane surface is required to improve its conductivity and permselectivity as well as its stabilities, including mechanical, chemical, and thermal stabilities (Khoiruddin, Ariono et al. 2017). Their separation ability depends not only by sieving mechanism, but also the electrolyte diffusion due to the exertion of electrostatic repulsive force against the electrolyte solute (Tsuru, Nakao et al. 1991). One of the most importance properties of charged membranes is their swelling behavior. Swelling is a dissolution process of a polymer in a defined solvent. It is greatly affected by the ionization of functional groups along the the polymer chain as well as the ionization of crosslinking agent molecules (Pieróg, Gierszewska-Drużyńska et al. 2009). In swelling membrane, the swollen polymer networks with pore/mesh of molecular size, usually between 20 and 100 Å (Peppas 1988). The mass transport of solutes in charged swelling membrane is based on the diffusivity of the penetrants into the mesh of the membrane.

In polyelectrolyte membrane, like PVA membrane, permeability mainly depends on the ions' mobility and their affinity with the membrane (Sun, Wu et al. 2014). Hydrophilic modification by blending PVA with other suitable hydrophilic polymers is one of alternative methods to improve the membrane affinity with the ions. Several modifications of PVA based ultrafiltration membrane have been studied (Yeom and Lee 1996, Mühlebach, Müller et al. 1997, Vauclair, Tarjus et al. 1997, Kim, Park et al. 2005, Wu, Lin et al. 2006, Wu, Gu et al. 2012, Josh, Haik et al. 2013, Jose, Shehzad et al. 2014). However, most of those studies used polyacrylonitrile (PAA) as additive. The use of polyallylamine (PAAm) as additive in PVA membrane preparation has not been found elsewhere. In this work, PVA/PAAm membrane was prepared by phase inversion method with glutaraldehyde as crosslinking agent. The addition of crosslinking agent is important to control the swelling behavior on the membrane. Meanwhile, NaCl and CaCl₂ were chosen as solutes, either as a single or double solute. This work then focused on the investigation of solute diffusion through PVA/PAAm membrane. The effect of PAAm addition and crosslinking ratio to membrane swelling degree was studied. In addition, the effect of membrane swelling to membrane performance, such as flux, rejection, and solute diffusion was also discussed.

EXPERIMENTAL

Membrane Preparation

Membrane was prepared from a mixture of PVA and PAAm with glutaraldehyde as

crosslinking agent. First, 10%-w PVA solution was heated until 90°C for two hours before cooled to 40°C. The PVA solution was mixed with PAAm, sulfate acid as catalyst, acetic acid as buffer, glutaraldehyde as crosslinking agent, and methanol as quencher. The composition of glutaraldehyde should be controlled to produce membrane with crosslinking ratio from 0.006 to 0.012 mol glutaraldehyde per mol PVA, as shown in Table 1. The mixed solution was casted on the Plexiglas and then dried in room temperature for about 6 days. After being dried, membrane was soaked in water for 24 hours to remove acid and methanol residual.

Table 1. Variation of membrane concentration and crosslinking ratio

PAAm/PVA (w/w)	Crosslinking ratio
0.04	0.006
	0.008
	0.010
	0.012
0.08	0.006
	0.008
	0.010
	0.012
0.12	0.006
	0.008
	0.010
	0.012

Membrane Characterization

Membrane characterization was conducted to calculate the swelling degree of membrane by measuring membrane weight in the air and in n-hexane solution. Before characterized, membrane was cut to 2x2 cm² sample. Mass of membrane sample

was measured in the air and in n-hexane solution. Measurements were carried out at 25°C. The degree of swelling was calculated using following equation (Geens, Van der Bruggen et al. 2004).

$$Q = \frac{(\omega_a - \omega_h)/\rho_h}{\omega_p/\rho_p} \quad (1)$$

where Q is membrane swelling degree, ω_p is mass of dried membrane sample (g), ω_a is mass of membrane sample in the air (g), ω_h is mass of membrane sample in n-hexane (g), ρ_p is PVA density (g/cm³), and ρ_h is n-hexane density (g/cm³).

Diffusion Experiment

Diffusion experiment was conducted to determine diffusion performance through PVA/PAAm membrane. There are two types of solution were used in the diffusion experiment: (a) single solute solution of sodium chloride (NaCl) and calcium chloride (CaCl₂), (b) double solute solution (mixture of NaCl and CaCl₂). Variation of solute concentration on the diffusion experiment can be seen in Table 2.

Table 2. Variation of diffusion experiment

Solute	Membrane thickness (cm)	Solute concentration (mmol/L)	
		NaCl	CaCl ₂
NaCl	0.03-0.07	52	-
CaCl ₂	0.03-0.07	-	52
Mixed solution A	0.03-0.07	26	26
Mixed solution B	0.03-0.07	52	52




Fig. 1: Schematic illustration of experimental set-up

Fig.1 shows the experimental set-up of this work. First, feed tank D was filled with 6 L of electrolyte solution (NaCl, CaCl₂, or the mixture of NaCl and CaCl₂) while tank B was filled with aqua dm and cooler C was filled with cooling water. G2 valve was opened with flow rate about 0.3 mL/s until bottom part of module A was filled with water. Then, G1 valve was opened and pump was turned on until feed solution filled the top of module A. A 100 mL of permeate was taken to analyze the solute concentration. For single solute solution, permeate concentration was measured by argentometric method, while permeate from double solute solution was analyzed using atomic absorption spectroscopy (AAS).

The diffusion coefficient of Na⁺ and Ca²⁺ solutes was calculated by following equation:

$$D_i = \left(\frac{RT}{F} \right) u_i \quad (2)$$

Here, R is universal gas constant, T is absolute temperature, F is Faraday number, and u_i is ion mobility of i .

RESULTS AND DISCUSSION

Membrane Characterization

In this work, PAAm was chosen as additive due to its hydrophilicity at normal

and acid condition. Besides, the addition of PAAm is able to improve membrane affinity and selectivity (Harsch, Calderon et al. 2000, Hamerli, Weigel et al. 2003, Dejeu, Lakard et al. 2009). Meanwhile glutaraldehyde was used as crosslinking agent with crosslinking ratio of 0.006-0.012 mol glutaraldehyde per mol PVA. The crosslinking agent was added to control the swelling formation in PVA membrane. The PVA/PAAm membrane was characterized to study the relation of crosslinking ratio and PAAm addition to membrane swelling degree.




Fig. 2: Membrane swelling degree as the function of crosslinking ratio and membrane concentration

Fig.2 shows that crosslinking ratio gave no significant effect to membrane swelling degree. The swelling degree was only




Fig. 3: Flux and rejection of Na^+ ions as a function of membrane thickness

slightly changed with the increase of crosslinking ratio. Meanwhile, the increase of PAAm concentration led to the increase of membrane swelling degree. The improvement could be due to additional sites like carboxylic acid groups from PAAm which strongly associated with membrane hydrophilicity (Jose, Shehzad et al. 2014, Khoiruddin, Ariono et al. 2017). The increase of hydrophilicity of membrane then led to the increase of water molecules that penetrate thorough membrane.

Diffusion of Single Solute

Membrane thickness can be used to indicate membrane swelling degree, where the increase of membrane thickness represents higher swelling degree. In homogeneous membrane, the permeability is greatly affected by membrane diffusivity and solubility, while independent to the membrane thickness. The diffusivity is uniform throughout the entire membrane. Meanwhile, for membrane with two or

more different structure layers with different permeabilities, the overall permeability is affected by membrane thickness. It is due to the presence of boundary resistance between the structure layers (Hwang and Kammermeyer 1974).

Fig.3 and Fig.4 show the effect of PVA/PAAm membrane thickness on the membrane flux and rejection for single solute diffusion. It can be seen that flux for both Na^+ and Ca^{2+} were decreased with the increase of membrane thickness. The flux obtained when using the thinnest membrane (0.03 cm) was approximately three times that of the thickest membrane (0.07 cm). Meanwhile, the Na^+ and Ca^{2+} rejection were increased 0.5-0.8%. These results were in agreement with previous studies (Aptel, Cuny et al. 1974, Qunhui, Ohya et al. 1995, Sridhar, Srinivasan et al. 2003, Kanti, Srigowri et al. 2004, Villaluenga, Khayet et al. 2005) where the increase of membrane thickness led to the increase of solute rejection.




Fig. 4: Flux and rejection of Ca^{2+} ions as a function of membrane thickness

Corresponds to the flux and rejection data in Fig.3 and Fig.4, the diffusion coefficients for both Na^+ and Ca^{2+} were decreased with the increase of swelling degree, as shown in Fig.5. Higher swelling degree was obtained by the increase of PAAm composition. As mentioned above, the addition of PAAm increase membrane hydrophilicity, thus higher amount of water penetrated to the membrane pores. The existence of the water molecules in the membrane pores made solutes difficult to penetrate through the membrane. Therefore, solute rejection was increased at higher swelling degree.

Furthermore, Fig.5 shows that diffusion coefficient for Na^+ and Ca^{2+} between 4.2564×10^{-6} to $6.8748 \times 10^{-6} \text{ cm}^2/\text{s}$. These results were compatible with diffusion coefficient that proposed by Schogl (Schlogl 1953), where diffusion coefficient of solute in membrane with water volume fraction more than 50% is about $10^{-6} \text{ cm}^2/\text{s}$. From Fig.5, it can be seen that the diffusion coefficients of Na^+ were higher than Ca^{2+} . It

means that Na^+ ions have higher mobility than Ca^{2+} ions since small molecules diffuse faster in solids than large molecules.




Fig. 5: Diffusion coefficients of Na^+ and Ca^{2+} as single solute

Diffusion of Double Solute

Fig.6 and Fig.7 show the effect of membrane thickness on the membrane flux and rejection for double solute diffusion. Mixed solution A consisted of 26 mmol/L Na^+ and 26 mmol/L Ca^{2+} , while mixed solution B consisted of 52 mmol/L Na^+ and 52 mmol/L Ca^{2+} . Same as single solute diffusion, flux was decreased and rejection




Fig. 6: Effect of membrane thickness on (a) flux and (b) rejection of solution A




Fig. 7: Effect of membrane thickness on (a) flux and (b) rejection of solution B

Table 3. Diffusion coefficient for double solute

Solute concentration in feed (mmol/L)		Q	D x 10 ⁶ (cm ² /s)	
NaCl	CaCl ₂		NaCl	CaCl ₂
26	26	4.577	7.783	3.972
		5.337	7.774	4.310
		6.614	6.775	3.623
52	52	4.577	7.820	3.695
		5.337	8.026	3.579
		6.614	7.182	3.590

was increased with the increase of membrane thickness.

The diffusion coefficients for double solute diffusion were calculated by same method as single solute diffusion. The diffusion coefficients of double solute diffusion are presented in Table 3.

In two solute diffusion, there is a positive or a negative influence on each other solute transport rate. The interaction of the solutes also has a significant effect on the sorption and penetration of the solute to the membrane (Izák, Hovorka et al. 2007). Compared to single solute diffusion,

diffusion coefficient of Na^+ was increased and diffusion coefficient of Ca^{2+} was decreased on double solute diffusion (Table 4). It was due to higher affinity between Na^+ and PVA/PAAm membrane and smaller size of NaCl molecules that led to higher rejection of Ca^{2+} ions. While Ca^{2+} ions were rejected, Na^+ ions moved more easily, thus coefficient diffusion of Na^+ was increased. Moreover, diffusion coefficient was also affected by solute concentration. By using lower concentration of NaCl and CaCl_2 , diffusion coefficient of Na^+ was increased while diffusion coefficient of Ca^{2+} was decreased. When the amount of Na^+ and Ca^{2+} ions were low, the interaction of ions and membrane charge decreased that led to the decrease of Ca^{2+} rejection and Na^+ mobility.

CONCLUSION

In this work, PVA membrane was prepared by phase inversion method with the addition of PAAm to increase its hydrophilicity and glutaraldehyde as crosslinking agent to control the membrane swelling. The results showed that the increase of PAAm concentration led to increase of membrane swelling degree. The addition of PAAm with concentration of 4%, 8%, and 12% produced membrane with swelling degree 4.577, 5.337, and 6.614, respectively. Meanwhile, the swelling degree was almost constant for all crosslinking ratios. For both single and double solutes, diffusion of Na^+ and Ca^{2+} were slightly decreased with the increase of swelling degree. However, in double solute diffusion, there was interaction between Na^+ , Ca^{2+} , and

membrane that made Na^+ ions moved faster and Ca^{2+} ions moved slower compared to single solute diffusion. In addition, diffusion coefficient of Na^+ was increased while diffusion coefficient of Ca^{2+} was decreased with the increase of solute concentration.

ACKNOWLEDGMENTS

The authors would like to thank the Institut Teknologi Bandung (ITB), Indonesia for financial support through Program Penelitian, Pengabdian kepada Masyarakat, dan Inovasi (P3MI).

REFERENCES

1. Aptel, P., J. Cuny, J. Jozefonvicz, G. Morel and J. Neel (1974). Liquid transport through membranes prepared by grafting of polar monomers onto poly(tetrafluoroethylene) films. II. Some factors determining pervaporation rate and selectivity. *J. Appl. Polym. Sci.* 18(2): 351-364.
2. Ariono, D., P. T. P. Aryanti, S. Subagjo and I. G. Wenten (2017). The effect of polymer concentration on flux stability of polysulfone membrane, AIP Conf. Proceed. 788(1):030048(1-10).
3. Aryanti, P. T. P., Khoiruddin and I. G. Wenten (2013). Influence of Additives on Polysulfone-Based Ultrafiltration Membrane Performance during Peat Water Filtration. *J. Water Sustain.* 3(2): 85-96.
4. Aryanti, P. T. P., R. Yustiana, R. E. D. Purnama and I. G. Wenten (2015). Performance and characterization of

-
- PEG400 modified PVC ultrafiltration membrane. *Membr. Water Treat.* 6(5): 379-392.
5. Asatekin, A., S. Kang, M. Elimelech and A. M. Mayes (2007). Anti-fouling ultrafiltration membranes containing polyacrylonitrile-graft-poly(ethylene oxide) comb copolymer additives. *J. Membr. Sci.* 298(1–2): 136-146.
 6. Dejeu, J., B. Lakard, P. Fievet and S. Lakard (2009). Characterization of charge properties of an ultrafiltration membrane modified by surface grafting of poly(allylamine) hydrochloride. *J. Colloid Interface Sci.* 333(1): 335-340.
 7. Du, J. R., S. Peldszus, P. M. Huck and X. Feng (2009). Modification of poly(vinylidene fluoride) ultrafiltration membranes with poly(vinyl alcohol) for fouling control in drinking water treatment. *Water Res.* 43(18): 4559-4568.
 8. Geens, J., B. Van der Bruggen and C. Vandecasteele (2004). Characterisation of the solvent stability of polymeric nanofiltration membranes by measurement of contact angles and swelling. *Chem. Eng. Sci.* 59(5): 1161-1164.
 9. Hamerli, P., T. Weigel, T. Groth and D. Paul (2003). Surface properties of and cell adhesion onto allylamine-plasma-coated polyethyleneterephthalat membranes. *Biomaterials* 24(22): 3989-3999.
 10. Hamid, N. A. A., A. F. Ismail, T. Matsuura, A. W. Zularisam, W. J. Lau, E. Yuliwati and M. S. Abdullah (2011). Morphological and separation performance study of polysulfone/titanium dioxide (PSF/TiO₂) ultrafiltration membranes for humic acid removal. *Desalination* 273(1): 85-92.
 11. Harsch, A., J. Calderon, R. B. Timmons and G. W. Gross (2000). Pulsed plasma deposition of allylamine on polysiloxane: a stable surface for neuronal cell adhesion. *J. Neurosci. Methods* 98(2): 135-144.
 12. Himma, N. F., S. Anisah, N. Prasetya and I. G. Wenten (2016). Advances in preparation, modification, and application of polypropylene membrane. *J. Polym. Eng.* 36(4): 329-362.
 13. Hwang, S.-T. and K. Kammermeyer (1974). Effect of Thickness on Permeability. *Permeability of Plastic Films and Coatings: To Gases, Vapors, and Liquids.* H. B. Hopfenberg. Boston, MA, Springer US: 197-205.
 14. Izák, P., Š. Hovorka, T. Bartovský, L. Bartovská and J. G. Crespo (2007). Swelling of polymeric membranes in room temperature ionic liquids. *J. Membr. Sci.* 296(1–2): 131-138.
 15. Jose, J., F. Shehzad and M. A. Al-Harathi (2014). Preparation method and physical, mechanical, thermal characterization of poly(vinyl alcohol)/poly(acrylic acid) blends. *Polym. Bull.* 71(11): 2787-2802.
 16. Josh, V., M. Y. Haik, A. I. Ayesh, M. A. Mohsin and Y. Haik (2013). Electrical properties of sorbitol-doped poly(vinyl alcohol)-poly(acrylamide-co-acrylic acid) polymer membranes. *J. Appl. Polym. Sci.* 128(6): 3861-3869.
 17. Kanti, P., K. Srigowri, J. Madhuri, B. Smitha and S. Sridhar (2004). Dehydration of ethanol through blend
-

-
- membranes of chitosan and sodium alginate by pervaporation. *Sep. Purif. Technol.* 40(3): 259-266.
18. Khoiruddin, D. Ariono, Subagjo and I. G. Wenten (2017). Surface modification of ion-exchange membranes: Methods, characteristics, and performance. *J. Appl. Polym. Sci.*: 45540 (1-13).
19. Khoiruddin, I. N. Widiassa and I. G. Wenten (2014). Removal of inorganic contaminants in sugar refining process using electrodeionization. *J. Food Eng.* 133: 40-45.
20. Kim, D. S., H. B. Park, J. W. Rhim and Y. M. Lee (2005). Proton conductivity and methanol transport behavior of cross-linked PVA/PAA/silica hybrid membranes. *Solid State Ionics* 176(1): 117-126.
21. Moghimifar, V., A. Raisi and A. Aroujalian (2014). Surface modification of polyethersulfone ultrafiltration membranes by corona plasma-assisted coating TiO₂ nanoparticles. *J. Membr. Sci.* 461(Supplement C): 69-80.
22. Mühlebach, A., B. Müller, C. Pharisa, M. Hofmann, B. Seiferling and D. Guerry (1997). New water-soluble photo crosslinkable polymers based on modified poly(vinyl alcohol). *J. Polym. Sci., Part A: Polym. Chem.* 35(16): 3603-3611.
23. Peppas, N. A. (1988). *Hydrogels in medicine and pharmacy*, CRC press Boca Raton, FL.
24. Pieróg, M., M. Gierszewska-Drużyńska and J. Ostrowska-Czubenko (2009). Effect of ionic crosslinking agents on swelling behavior of chitosan hydrogel membranes. *Prog. Chem. Appl. Chitin Derivatives* 75: 82.
25. Qunhui, G., H. Ohya and Y. Negishi (1995). Investigation of the permselectivity of chitosan membrane used in pervaporation separation II. Influences of temperature and membrane thickness. *J. Membr. Sci.* 98(3): 223-232.
26. Rahimpour, A. and S. S. Madaeni (2007). Polyethersulfone (PES)/cellulose acetate phthalate (CAP) blend ultrafiltration membranes: Preparation, morphology, performance and antifouling properties. *J. Membr. Sci.* 305(1-2): 299-312.
27. Razmjou, A., J. Mansouri and V. Chen (2011). The effects of mechanical and chemical modification of TiO₂ nanoparticles on the surface chemistry, structure and fouling performance of PES ultrafiltration membranes. *J. Membr. Sci.* 378(1-2): 73-84.
28. Schlögl, R. (1953). Ion mobility in exchangers. *J. Electrochem.* 57(3): 195-201.
29. Sridhar, S., T. Srinivasan, U. Virendra and A. A. Khan (2003). Pervaporation of ketazine aqueous layer in production of hydrazine hydrate by peroxide process. *Chem. Eng. J.* 94(1): 51-56.
30. Sun, F., C. Wu, Y. Wu and T. Xu (2014). Porous BPPO-based membranes modified by multisilicon copolymer for application in diffusion dialysis. *J. Membr. Sci.* 450: 103-110.
31. Tsuru, T., S.-i. Nakao and S. Kimura (1991). Calculation of ion rejection by extended Nernst-Planck equation with charged reverse osmosis membranes for single and mixed electrolyte solutions. *J. Chem. Eng. Jpn.* 24(4): 511-517.
-

32. Vauclair, C., H. Tarjus and P. Schaetzel (1997). Permselective properties of PVA-PAA blended membrane used for dehydration of fusel oil by pervaporation. *J. Membr. Sci.* 125(2): 293-301.
 33. Villaluenga, J. P. G., M. Khayet, P. Godino, B. Seoane and J. I. Mengual (2005). Analysis of the membrane thickness effect on the pervaporation separation of methanol/methyl tertiary butyl ether mixtures. *Sep. Purif. Technol.* 47(1): 80-87.
 34. Wardani, A. K., A. N. Hakim, Khoiruddin, W. Destifen, A. Goenawan and I. G. Wenten (2017). Study on the influence of applied voltage and feed concentration on the performance of electrodeionization in nickel recovery from electroplating wastewater, AIP Conf.Proceed. 1805(1):030004(1-7).
 35. Wardani, A. K., A. N. Hakim, Khoiruddin and I. G. Wenten (2017). Combined ultrafiltration-electrodeionization technique for production of high purity water. *Water Science and Technology* 75(12): 2891-2899.
 36. Wu, C., J. Gu, Y. Wu, J. Luo, T. Xu and Y. Zhang (2012). Carboxylic acid type PVA-based hybrid membranes for alkali recovery using diffusion dialysis. *Sep. Purif. Technol.* 92: 21-29.
 37. Wu, G. M., S. J. Lin and C. C. Yang (2006). Preparation and characterization of PVA/PAA membranes for solid polymer electrolytes. *J. Membr. Sci.* 275(1): 127-133.
 38. Yeom, C.-K. and K.-H. Lee (1996). Pervaporation separation of water-acetic acid mixtures through poly(vinyl alcohol) membranes crosslinked with glutaraldehyde. *J. Membr. Sci.* 109(2): 257-265.
-